

Electronics

Tweezers
7 Plastic Replaceable tips Tweezers



Very fine, curved tips

A 5" 130 mm B 0.025" 0.6 mm C 0.025" 0.6 mm



A7CP Replaceable tips set

General notes

- PEEK polyetheretherketone reinforced with carbon fibre
- very hard, rigid, high tensile and flexural strength, very high wear resistance
- high heat capability (260-300°C), good dimension stability, low thermal linear expansion coefficient
- excellent resistance to chemicals and aggressive agents, excellent resistance to thermal ageing

- ESD-safe material
- typical applications include handling of components in cleaning/chemical/assembly processes also at high temperature (soldering)

Mechanical properties

Flexural modulus +23°C:	21400 MPa	ISO 178 ASTM D 790
Flexural strength +23°C:	350 MPa	ISO 178 ASTM D 790
Tensile modulus +23°C:	24000 MPa	ISO 527 ASTM D 638
Tensile strength +23°C:	190 MPa	ISO 527 ASTM D 638
Izod - Impact strength (notched) +23°C	65 J/m	ISO 180/4AASTM D 256

Thermal properties

Temp. of defl. under load (1.80 MPa):	300°C	ISO 75 ASTM D648
tomp. or don: dildor load (1.00 km a).	000 0	100 1010 IN DO 10

Continuous Use Temperature: 260°C 20'000 h

Short Time Temperature 300°C

Electrical properties

Surface resistivity: 10 5 -10 6 Ohm

Decay time: < 0.2 sec 1000-10 V

Other properties

Density	1.39 g/ccm	ISO 1183
Water absorption in water 23°C (24h)	0.01%	ISO 62

© IDEAL-TEK SA Credits